

TECHINAL CARD

Supplier:	DORUKLAR ÖRME	Date:	7.07.2023
Article:	24/1 COMBED %100 COTTON 180 CM 180 /170GSM	INVOICE NUMBER	
Composition :	%100 COTTON JERSEY FERMO		
Type of dyeing:	REACTIVE	dyestuff used:	

I. PHYSICAL

Width cm (total) :180+- 2	Width cm (usable) :	
Weight gr/m ² :180 +- 5	care label instructions:	
Construction : %100 COTTON	woven:	knitted: X
Yarn Count : 24/1 COMBED	warp:	weft:
threads/picks (per inch):	warp:	weft:
skew (wovens) maximum % :	Antistatic Finish:	YES/NO
δ		
Colour variation (maximum limits allowed):		
a) de=0,50 inside the roll and inside the lot :		
b) de=1,00 between the lots :		
spirality % (for knits)		

II. DIMENSIONAL STABILITY

	Warp	Weft
	length / BOY	width / EN
1. Shrinkage after washing according to the care symbols (DIN EN ISO 6330) % MELANGE	-3	-6
	Warp/length	Weft/width
2. Shrinkage after washing according to the care symbols (DIN EN ISO 6330) % COLORS	-4	-6

III. COLOR FASTNESS

	Dry	Wet
1. Color fastness to rubbing (DIN EN ISO 105 - X12) :	2-3	2-3
2. Color fastness to washing (DIN EN ISO 105 - C06) :		
2a.Colour Change:		
2b.Colour Staining:		Wool/Acrl./Pes/Nylon/Cot./Acetate
3. Color fastness to dry cleaning (DIN EN ISO 105 - D01) : * when Dry Cleaning is recommended on care label		
	LIGHT COLOURS:	
	MEDIUM:	
	DARK COLOURS:	

IV. TWISTING

	-2%
--	-----



V. PACKAGING INFORMATION

Attention to creases, wrinkles, folding marks, when folding the rolls	ROLL
-----------------------------------------------------------------------	------

VI. OTHER

Fabric must not have more than total of 12 faults per 100 meters	
Oeko Tex Standard 100	YES
AZO FREE CERTIFICATE	

WE HEREBY CONFIRM THAT THE GOODS WILL BE PRODUCED ACCORDING TO THIS DATA



WASH INSTRUCTION

MUST BE WASH 40C